

Mildew-resistant silicone sealant

Description

DOMOSIL-S is a mildew-resistant silicone for highly demanding jobs, providing:

- High mechanical resistance.
- Resistance to temperature fluctuations from -60°C to +220°C.
- Excellent bonding to any kind of non porous building material.
- Great endurance to ageing.
- Prevention of mildew and fungi growth.

Fields of application

DOMOSIL-S is suitable for sealing vertical and horizontal joints 3-40 mm wide on non-porous material surfaces such as glass, aluminium, porcelain (tiles etc) and non-porous ceramics, in indoor or outdoor areas. It is applied in high humidity areas (kitchens, bathrooms etc) as well as hospitals, biology and microbiology labs etc.

It prevents the growth of mildew or fungi, which cause black spots and stains in such areas.

It is not recommended for use in aquariums because of the fungicide it contains.

Technical data

Base:	silicone
Color:	transparent, white
Skin formation:	after 10-15 min
Maturation speed:	2,0-2,5 mm/day
Hardness according to SHORE A:	19 ± 2

Directions for use

1. Substrate

Substrate must be free of dust, loose particles, grease etc. It is advisable that the joint is cleaned up using a paintbrush or a wire brush and then air-blasted.

To avoid undesirable soiling at joint edges, a self-adhesive paper-tape is applied alongside the edges and then removed immediately after sealing the joint (before skin formation).

2. Application

Insert cartridge in the special gun and cut nozzle in a slant way so that as it does not fit into the joint but just touches and slides along the edges.

Silicon is applied by driving the cartridge alongside the joint axis at a 45° angle.

While still fresh, silicone is leveled using a trowel or by finger.

Cleaning of tools:

Tools must be cleaned thoroughly with water whilst material is still fresh. If material is hardened, tools may be mechanically cleaned.

Consumption

- Joint 10mm x 10mm:
1 cartridge / 3 m of joint length.
- Joint 5mm x 5mm:
1 cartridge / 12 m of joint length.

DOMOSIL-S



Packaging

Cartridges of 280 ml.

Storage

Shelf-life is 12 months, in dry and frost-free conditions.

Remarks

- Ambient temperature during application must be between -10°C and $+60^{\circ}\text{C}$.

J M Vassallo Vibro Steel Limited, Vibro Complex, Mdina Road, Zebbug ZBG 9019, Malta

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the department of Research and Development of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical data sheet automatically cancels any previous one concerning the same product.

